

Laboratory Test Sheet

PARTICLE SIZE DISTRIBUTION BS 812 : PART 103 : 1985
Method 7.2 / 7.3*

Client :	Site :
Client Ref. :	Job No. :
Lab. Ref. :	Date Received :
Supplier :	Source :
Material Type : Sub-base	Specification :
Material Name : Type 1 Sub-base	Aggregate Type :

Tray No.	Tray Wt.	Tray + Wet Wt.
Tray + Dry Wt.	Unwashed Dry Wt.(M1)	

Washed Dry Wt+Tray	Washed Dry Wt.(M2)	Loss of Fines (M3) (M1-M2)
--------------------	--------------------	----------------------------

BS Sieve	Max. Wt. 2	Weight Retained (g) 3		% Ret. 100	% Passing		Specification % Passing
		Increments	Total		Actual	Reported	
200 mm	5000 g						
150 mm	5000 g						
125 mm	5000 g						
100 mm	5000 g						
90 mm	5000 g						
75 mm	5000 g						
63 mm	5000 g						
50 mm	5000 g						
37.5 mm	4000 g						
28 mm	3000 g						
20 mm	2500 g						
Rifle Weight passing 20 mm Sieve =		Weight after Rifle=			Rifle Factor =		
14 mm	2000 g						
10 mm	1500 g						
6.3 mm	1000 g						
5 mm	750 g						
Rifle Weight passing 5 mm Test Sieve =		Weight after Rifle=			Rifle Factor =		
3.35 mm	550 g						
2.36 mm	450 g						
1.18 mm	300 g						
600 um	225 g						
425 um	180 g						
300 um	150 g						
212 um	130 g						
150 um	110 g						
75 um	75 g						
Passing 75 µm							
Loss of Fines (M3)							
TOTALS					Total in column 3 must = mass M1		

Comments :

Tested By :	Date :	Checked By :	Date :
-------------	--------	--------------	--------

Check Level (1 / 2 / 3)*

- Notes *
- * Delete as applicable.
 - 1 - Use attached form for interim constant dry weight checks.
 - 2 - For 300 mm dia. Sieves.
 - 3- Where weight on the sieve is greater than allowed each increment sieved must be recorded on this form then totalled.
 - 4 - Particles to be weighed to 0.1 % of their mass to maximum accuracy of 0.01 g.